STERNE, KESSLER, GOLDSTEIN & FOX P.L.L.C.

ATTORNEYS AT LAW

IIOO NEW YORK AVENUE, N.W., SUITE 600 WASHINGTON, D.C. 20005-3934

(202) 371-2600

FACSIMILE. (202) 371-2540, (202) 371-6566

ROBERT GREENE STERNE EDWARD J KESSLER . JORGE A GOLDSTEIN SAMUEL L FOX DAVID K.S CORNWELL ROBERT W ESMOND TRACY-GENE G. DURKIN MICHELE A CIMBALA MICHAEL B RAY ROBERT E SOKOHL ERIC K STEFFE
MICHAEL O LEE
STEVEN R LUDWIG
JOHN M COVERT*
LINDA E ALCORN
RAZ E FLESHNER
ROBERT C MILLONIG
MICHAEL V MESSINGER
JUDITH U. KIM
TIMOTHY J SHEA, JR

DONALD R MCPHAIL
PATRICK E GARRETT
STEPHEN G. WHITESIDE
JEFFREY T HELVEY*
HEIDI L KRAUS
JEFFREY R KURIN
RAYMOND MILLIEN
PATRICK D O'BRIEN
LAWRENCE B BUGAISKY
CRYSTAL D SAYLES*

EDWARD W YEE
ALBERT L FERRO*
DONALD R BANOWIT*
PETER A JACKMAN
MOLLY A MCCALL
TERESA U MEDLER
JEFFREY S. WEAVER
KRISTIN K VIDOVICH
ANDREW S. ROBERTS*
KENDRICK P. PATTERSON*

DONALD J FEATHERSTONE
KAREN R. MARKOWICZ**
GRANT E REED**
SUZANNE E ZISKA**
BRIAN J DEL BUONO**
VINCENT L CAPUANO**
ANDREA J KAMAGE**
NANCY J DEGEN**

ROBERT H BENSON*

*BAR OTHER THAN D C
**REGISTERED PATENT AGENTS

November 10, 1999

WRITER'S DIRECT NUMBER: (202) 789-5519 INTERNET ADDRESS: KVIDOVIC@SKGF.COM

Box Patent Application

Assistant Commissioner for Patents

Washington, D.C. 20231

Re: New U.S. Non-Provisional Utility Patent Application

Appl. No. To be assigned; Filed: Herewith For: Recovering Metals from Soil

Inventors:

Chaney et al.

Our Ref:

1797.0090005/RWE/KKV

Sir:

The following documents are forwarded herewith for appropriate action by the U.S. Patent and Trademark Office:

1. U.S. Utility Patent Application entitled:

Recovering Metals from Soil

and naming as inventors:

Rufus L. Chaney Jayce Scott Angle Yin-Ming Li Alan J.M. Baker

the application comprising:



Assistant Commissioner for Patents November 10, 1999 Page 2

a specification containing:

- (i) 30 pages of description prior to the claims;
- (ii) 7 pages of claims (47 claims);
- (iii) a one (1) page abstract;
- 2. USPTO Utility Patent Application Transmittal Form PTO/SB/05;
- 3. 37 C.F.R. § 1.136(a)(3) Authorization to Treat a Reply As Incorporating An Extension of Time (in duplicate); and
- 4. Two (2) return postcards.

It is respectfully requested that, of the two attached postcards, one be stamped with the filing date of these documents and returned to our courier, and the other, prepaid postcard, be stamped with the filing date and unofficial application number and returned as soon as possible.

This patent application is being submitted under 37 C.F.R. § 1.53(b) without Declaration and without filing fee.

Respectfully submitted,

STERNE, KESSLER, GOLDSTEIN & FOX P.L.L.C.

Kristin K. Vidovich Attorney for Applicants Registration No. 41,448

Rustin K. Vidora

KKV/pcd Encls.

PTO/SB/05 (2/98)
Approved for use through 09/30/2000. OMB 0651-0032
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE —
of information unless it displays a valid OMB control number

Under the Paperwork Reducti	ion Act of 1222, no betsoms are led	uned to respond to a co	Attorney Docket No. 1797.0090005/RWE/KKV					
			First Inventor or					
UTILITY PAT	TENT APPLICATION TRA	NSMITTAL	Application Identifier Rufus L. Chaney					
(Only for new non	provisional applications under 37	CFR § 1.53(b))	Title Recovering Metals from Soil					
			Express Mail Label No.	Ť				
								
	PPLICATION ELEMENTS 600 concerning utility patent applic	ation contents.	ASSISTANT CO ADDRESS TO: Box Patent A Washington,		atents			
	nittal Form (e.g., PTO/SB/17 amal, and a duplicate for fee proces		6. Microfiche Comput	er Program (A	Appendix)			
2. Specifica	tion [Total Pages	38]	7. Nucleotide and/or Amin applicable, all necessary		ence Submission (if			
- Descriptive title - Cross Reference	s to Related Applications		a. Computer Reada	able Copy				
 Reference to Mic 	ding Fed sponsored R & D crofiche Appendix		b. Paper Copy (ide	ntical to com	nuter conv)			
- Background of ti - Brief Summary of			b. Taper copy (ide	inical to com	puter copy)			
- Detailed Descrip - Claim(s) - Abstract of the D	otion		c. Statement verify	ring identity of	of above copies			
3. Drawing(s)	(35 U.S.C. 113) [Total Sh	ets]	ACCOMPANYIN	NG APPLIC	ATION PARTS			
4. Oath or Decl	laration (Total Pages	1	8. Assignment Papers (co	ver sheet & doo	cument(s))			
-	executed (original or copy)	1	9. 37 CFR 3.73(b) Statem (when there is an assig		wer of Attorney			
b. ☐ Copy fro	om a prior application (37 (CFR 1.63(d)) (for	10. English Translation Do	ocument (if app	licable)			
	on/divisional with Box 17 complete x 5 below]	d)	11. Information Disclosure Statement (IDS)/PTO-		pies of IDS Citations			
i. 🔲	DELETION OF INVEN		12. Preliminary Amendme					
	Signed statement attached on named in the prior application		13. Two Return Receipt Po		503)			
	1.63(d)(2) and 1.33(b).		(Should be specifically		303)			
The entire disclos	n By Reference (useable of Box oure of the prior application, from we on is supplied under Box 4b, is cons	hich a copy of the	14. *Small Entity Statemen (PTO/SB/09-12)	ap	tatement filed in prior oplication, Status still proper and desired			
	the accompanying application and i							
			16. ☑ Other: 37 C.F.R. § 1.136(a)(3) Authorization					
			Other:					
			*NOTE FOR ITEMS 1 & 14. IN ORDER SMALL ENTITY STATEMENT IS REQUI PRIOR APPLICATION IS RELIED UPO	RED (37 C.F.R § 1	.27). EXCEPT IF ONE FILED IN A			
17. If a CONTINUE	NG APPLICATION, check	appropriate box, and su	pply the requisite information below o	md in a prelimin	ary amendment:			
☐ Continuation	_	_	Part (CIP) of prior applicati	•	•			
Prior application	n information: Examiner		Group/Art Unit:					
	1	8. CORRESPON	DENCE ADDRESS					
Customer N or Bar Code		omer No. or Attach	bar code label here)	or Corresp address	oondence below			
NAME	STERNE, KESSLER, GOLDSTEIN	& FOX P.L.L.C.						
	Attorneys at Law							
ADDRESS	Suite 600, 1100 New York Ave	nue, N.W.						
CITY	Washington	STATE	DC	ZIP CODE	20005-3934			
COUNTRY	USA	TELEPHONE	(202) 371-2600	FAX	(202) 371-2540			
1141 (D. O	-) W 1-41- W 777 1 1 1	1,						
NAME (Print/Ty)				,448				
SIGNATURE	Ruiten K. Vac	vu Date	NOV. 10, 1959		i			

Burden Hour Statement: this form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Recovering Metals from Soil

Background of the Invention

Statement as to Rights to Inventions Made Under Federally-Sponsored Research and Development

Part of the work performed during development of this invention utilized U.S. Government funds. The U.S. Government has certain rights in this invention.

Cross-Reference to Related Applications

This application is a continuation-in-part of U.S. Application No. 09/386,373, filed August 31, 1999, which is a continuation-in-part of U.S. Application No. 08/879,813, filed June 20, 1997, now U.S. Patent No. 5,944,872, which is a continuation of U.S. 08/470,440, filed June 6, 1995, now U.S. Patent No. 5,711,784, and this application claims priority to U.S. Provisional Application Nos. 60/109,443, filed November 23, 1998, and 60/107,797, filed on November 10, 1998. U.S. Patent Nos. 5,711,784 and 5,944,872, and U.S. Provisional Application Nos. 60/107,797 and 60/109,443 are herein incorporated by reference.

Field of the Invention

20

This invention pertains to methods for recovering metals, such as nickel and cobalt, from metal-rich soil using phytoextracting or phytomining techniques. Metals can be selectively extracted from soil by cultivating certain metal hyperaccumulating plants, such as *Alyssum* plants, on soil treated to adjust the pH.

10

5

Related Art

Industrial practices such as mining, smelting and disposing of manufacturing wastes have increased the concentrations of toxic metals in the environment. For example, at many nickel mining and smelting sites, levels of nickel and cobalt in soil have become so high that few plants survive, resulting in severe disruption of local ecosystems. Once nickel and cobalt enter soil, their removal is difficult since they are relatively immobile and they do not degrade into less toxic substances. The size of the areas affected by smelter and mine wastes are usually so large that engineering methods of soil remediation, such as soil removal and replacement, are too expensive to be practical (Cunningham *et al.*, "Phytoremediation of Contaminated Soils," *Trends Biotechnol. 13:* 393-397 (1995)).

The ability of certain plants to grow in metal-containing or metal-contaminated soil, and to actively accumulate heavy metals in their tissues, has created an interest in using such plants to extract metals from soil. Growing plants, including crops, on contaminated soil to extract contaminants is referred to as phytoextraction. This method is particularly effective in arable contaminated soils because it causes little disruption or dispersal, while preserving soil fertility and landscapes.

Nickel is one of the most widely found, and technologically important metals. It is a natural constituent in all soils, being particularly high in concentration in certain types of soil and geological materials such as serpentine, lateritic serpentine, ultramafic and meteor-derived soils. Cobalt, another valuable metal, has chemical and geological characteristics very similar to nickel and is generally found in the same soils. Other metals that may be found in such soils include those of the platinum and palladium families such as palladium, rhodium, ruthenium, platinum, iridium, osmium and rhenium, and metals such as selenium, zinc and cadmium.

15

5

10

20

10

15

20

25

30

Sites containing serpentine, lateritic serpentine, ultramafic and meteor-derived soils and materials can be conventionally mined or cultivated with metal-accumulating plants. Using such plants to extract metals from mineralized (geogenic) soils is referred to as phytomining.

U.S. Patent No. 5,364,451 to Raskin et al., is directed to a method of remediating polluted soils at a reduced cost. Raskin et al. remove metals from metal-rich soil by growing plants of the family Brassicaceae in the metal-rich soil. While Raskin et al. generally describe a variety of plants and a large number of metals that may be recovered, the examples mainly describe the recovery of chromium and lead from genetically altered plants. Thus, although promising, Raskin et al. offer little basis for an opportunity to proceed directly with soil phytomining or phytoextraction through plant growth or cultivation.

U.S. Patent No. 5,785,735 to Raskin et al., is also directed to methods of remediating polluted soils. Raskin et al. remove metals from metal-rich soil by growing crop and crop-related members of the plant family Brassicaceae in the metal-rich soil. The methods require the formation of a complex between the metal and a chelating agent added to the soil, the application of an electric field to the soil or a reduction in the pH of the soil. While Raskin et al. generally describe a variety of plants, the specification mainly describes the recovery of metals from genetically altered plants. Thus, again, Raskin et al. offer little basis for an opportunity to proceed directly with soil phytomining or phytoextraction through plant growth or cultivation.

Scientists recognize that increasing the pH of soil decreases the ability of farm crops to take-up heavy metals. U.S. Patent No. 5,711,784 to Chaney et al. reflects the belief in the art that reducing the pH of the soil "increases the phytoavailability of nickel and cobalt." As disclosed by Chaney et al., a "reduced pH increases solubility, and optimizes the release of these metals for absorption by the roots and translocation to the above-ground tissues of the plant." However, reducing the pH of the soil also renders the metals more mobile and may allow for further contamination of the site. Therefore, cultivating plants which are

hyperaccumulators of nickel, cobalt and other metals through phytoextraction or phytomining, is a desirable alternative as a means for recovering such metals.

Summary of the Invention

Accordingly, this invention relates to improved systems for recovering metals by phytomining or phytoextracting soils rich in metals.

The invention further relates to increasing nickel uptake by plants used in phytomining and phytoextraction by elevating the soil pH. Nickel is ultimately recovered from plant tissues at economically acceptable levels without further contaminating the nickel-containing site.

The invention further relates to lowering the pH in soils prior or subsequent to nickel recovery to collect, for example, cobalt or any other metal present in the metal-laden soil.

In a particular aspect of the invention, *Alyssum* plants are cultivated under favorable pH conditions to selectively accumulate certain metals relative to other metals.

The invention further relates to a method for selectively increasing the amount of at least one metal recovered from metal-containing soil comprising:

- (a) elevating or lowering the pH of the soil;
- (b) cultivating at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate at least one metal from the soil in above-ground tissue;
- (c) elevating the pH of the soil if the pH was lowered in step (a) or lowering the pH of the soil if the pH was elevated in step (a); and
- (d) cultivating the at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate at least one second metal from the soil in above-ground tissue.

The invention further relates to a method for recovering nickel from nickel-containing soil comprising:

15

10

5

20

- (a) elevating the pH of the soil;
- (b) cultivating at least one nickel-hyperaccumulator plant in the soil under conditions such that at least 0.1% of the above-ground tissue of said at least one plant, on a dry weight basis, is nickel;
 - (c) harvesting said at least one plant; and
 - (d) recovering nickel from said harvested plant.

The invention further relates to a method for recovering cobalt from cobalt-containing soil comprising:

- (a) lowering the pH of the soil;
- (b) cultivating at least one cobalt-hyperaccumulator plant in the soil under conditions such that at least 0.1% of the above-ground tissue of said at least one plant, on a dry weight basis, is cobalt;
 - (c) harvesting said at least one plant; and
 - (d) recovering cobalt from said harvested plant.

The invention further relates to the identification of new hyperaccumulating species of *Alyssum* whereby collected plants are screened by comparing nickel-uptake by the plants to nickel-uptake by the bench-mark nickel-hyperaccumulator *A. murale 103*. These new metal-hyperaccumulating species, cultivated on nickel-containing soil, accumulate nickel in above-ground tissue at a concentration of 1.55% or greater by weight based on the gross dry weight of the tissue.

The invention further relates to seeds of the Alyssum plant species.

The invention further relates to pollen of the Alyssum plant species.

The invention further relates to plants that have all the physiological and morphological characteristics of the *Alyssum* plant species.

The invention further relates to propagation material of the *Alyssum* plant species.

The invention further relates to a method for decontaminating metalcontaining soil, comprising cultivating at least one hyperaccumulator plant in metal-containing soil, whereby the concentration of metal in the above-ground

10

5

15

20

25

plant tissue of the at least one hyperaccumulator plant exceeds the concentration of metal in the soil by a factor of at least 2.

Detailed Description of the Preferred Embodiments

In the present invention, it was discovered that certain metals can be selectively recovered from metal-rich soil using phytoextraction or phytomining techniques employing plants classified as hyperaccumulators of metals. By cultivating selected plants on metal-containing soil, the metals absorbed by the roots can be translocated to above-ground tissues, such as the stems, leaves, flowers and other leaf and stem tissues. This feature facilitates recovery of the metal extracted from the soil. Metal concentrations can be as high as about 5.0% in above-ground plant tissues, when leaves are included, which renders the metal recovery very economical. However, recovering metal in concentrations of less than about 5.0%, such as about 4.0%, 3.0%, 2.5%, 1.0% or 0.1% remains useful. For example, a recovery of about 1.0% or more offers economic return for decontaminating polluted soil and for phytomining. A recovery of about 0.1% to about 1.0% of cobalt is sufficient to decontaminate polluted soil at a low cost, and a recovery of even less than about 0.1% of some metals can still effectively decontaminate polluted soils.

The invention further relates to a method for selectively increasing the amount of at least one metal recovered from metal-containing soil comprising:

- (a) elevating or lowering the pH of the soil;
- (b) cultivating at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate at least one metal from the soil in above-ground tissue;
- (c) elevating the pH of the soil if the pH was lowered in step (a) or lowering the pH of the soil if the pH was elevated in step (a); and

10

5

15

20

(d) cultivating the at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate at least one second metal from the soil in above-ground tissue.

The invention further relates to a method for recovering nickel from nickel-containing soil comprising:

- (a) elevating the pH of the soil;
- (b) cultivating at least one nickel-hyperaccumulator plant in the soil under conditions such that at least 0.1% of the above-ground tissue of said at least one plant, on a dry weight basis, is nickel;
 - (c) harvesting said at least one plant; and
 - (d) recovering nickel from said harvested plant.

The invention further relates to a method for recovering cobalt from cobalt-containing soil comprising:

- (a) lowering the pH of the soil;
- (b) cultivating at least one cobalt-hyperaccumulator plant in the soil under conditions such that at least 0.1% of the above-ground tissue of said at least one plant, on a dry weight basis, is cobalt;
 - (c) harvesting said at least one plant; and
 - (d) recovering cobalt from said harvested plant.

The invention further relates to the identification of new hyperaccumulating species of *Alyssum* whereby collected plants are screened by comparing nickel-uptake by the plants to nickel-uptake by the bench-mark nickel-hyperaccumulator *A. murale 103*. These new metal-hyperaccumulating species, cultivated on nickel-containing soil, accumulate nickel in above-ground tissue at a concentration of 1.55% or greater by weight based on the gross dry weight of the tissue.

The invention further relates to seeds of the Alyssum plant species.

The invention further relates to pollen of the Alyssum plant species.

The invention further relates to plants that have all the physiological and morphological characteristics of the *Alyssum* plant species.

10

5

15

20

25

10

15

The invention further relates to propagation material of the *Alyssum* plant species.

The invention further relates to a method for decontaminating metal-containing soil, comprising cultivating at least one hyperaccumulator plant in metal-containing soil, whereby the concentration of metal in the above-ground plant tissue of the at least one hyperaccumulator plant exceeds the concentration of metal in the soil by a factor of at least 2, preferably by a factor of 2, 3 or 4.

In a preferred aspect of the invention, nickel is selectively accumulated by growing one or more nickel-hyperaccumulating plants in metal-rich, e.g., nickel-rich, soil and elevating the pH of the soil. The pH of the soil may be elevated before, during or after the plants are cultivated. Preferably, the pH is elevated prior to plant cultivation. Thus, the invention relates to the surprising discovery that raising the pH of the metal-rich soil favors nickel accumulation in plant tissue over other metals. The soil pH can then be lowered to selectively accumulate, in the plant tissue, other metals such as cobalt. The preferred pH will depend, *inter alia*, upon the particular metal and the soil. For example, the preferred pH for nickel extraction ranges between about 6.3 and about 7.0 when the soil is a serpentine soil or when the soil contains high iron oxide levels. The most preferred pH ranges from about 6.3 to about 6.7. However, when the iron oxide level is low, a more alkaline pH may be used.

Cobalt extraction is also affected by the soil chemistry. For example, the most preferred pH for cobalt extraction is about 5.5 when aluminum and/or manganese are present in the soil. For metal extraction in general, the preferred pH ranges between about 5.5 and about 7.0.

Soil pH can be raised and lowered with bases and acids. Such bases and acids may be either naturally occurring or synthetic. To raise the pH, bases such as limestone (calcitic (CaCO₃) or dolomitic (CaMgCO₃)), lime (CaO), hydrated lime (Ca(OH)₂), industrial, municipal or agricultural alkaline by-products that contain any of the above bases or a limestone equivalent, or the like can be used. The phrase "limestone equivalent" is intended to encompass bases that have the

25

20

same alkalinity as limestone. To lower the pH, acids such as organic and inorganic acids can be used. Examples of such organic and inorganic acids include acetic acid, aqueous hydrogen chloride, aqueous sulfuric acid, sulfur, ammonium, urea-containing fertilizers, nitric acid, sulfide minerals, including, but not limited to, pyrite, and the like.

The amount of base or acid to add depends upon the existing pH of the soil and the soil chemistry. Methods used to determine the amount include, but are not limited to, adding acid or a base, such as CaCO₃, to the soil sample and measuring the resulting pH, then drawing a pH response curve to extrapolate the amount needed to obtain the desired pH.

After cultivation, the hyperaccumulator plant is harvested in a conventional fashion, i.e., by cutting the plant at soil level. The harvested materials are then left to dry in the field in the manner in which hay is dried. Alternatively, the harvested materials are dried in much the same fashion that alfalfa is dried, so as to remove most of the water present in the plant tissue by forced heated air drying. After drying, the plant tissue is collected by normal agricultural practices of hay-making, incinerated and reduced to an ash with or without energy recovery. Alternatively, the dried plant material may be hydrolyzed with concentrated acid to produce sugars and the metals recovered according to U.S. Patent Nos. 5,407,817, 5,571,703 and 5,779,164. The sugars may then be fermented to produce ethanol.

The resulting dried plant material may alternatively be further treated by known roasting, sintering or smelting methods which allow the metals in the ash or ore to be recovered according to conventional metal refining methods such as acid dissolution and electrowinning.

Conventional smelting, roasting and sintering temperatures from about 260°C to about 1000°C are sufficient to combust the dried plant material to oxidize and vaporize the organic material present and to prevent dioxin accumulation during incineration. The preferred temperature is sufficient to remove the organic carbon to free the ash. The most preferred temperature is

10

5

15

20

25

20

5

10

about 1000°C. The process leaves a residue of the accumulated metal with few contaminants known to interfere with metal refining. Further, it is expected that the concentration of other components in the ash will be much lower than with conventional mined ore concentrates. For example, serpentine laterite ores generally contain over 10,000 ppm (1%) Fe whereas a biomass obtained using phytomining techniques only contains about 100-500 ppm (0.01 - 0.05%) Fe.

By definition, nickel-hyperaccumulating plants accumulate at least about 1000 mg of nickel per 1 kg dry weight of plant tissue (obtained from a plant grown in soil where the plant naturally occurs). Similarly, cobalt-hyperaccumulating plants are defined as plants that accumulate at least about 1000 mg of cobalt per 1 kg dry weight of plant tissue (obtained from a plant grown in soil where the plant naturally occurs). However, zinc- and manganese-hyperaccumulators are defined as plants that accumulate at least about 10,000 mg of zinc and manganese, respectively, per 1 kg dry weight of plant tissue (obtained from a plant grown in soil where the plant naturally occurs). Finally, cadmium-hyperaccumulators are defined as plants that accumulate at least about 100 mg cadmium per 1 kg dry weight of plant tissue (obtained from a plant grown in soil where the plant naturally occurs).

By screening a wide variety of plants, those of the *Alyssum* genus (Brassicaceae family) have been identified as hyperaccumulators of nickel. These plants also naturally accumulate cobalt and may accumulate metals such as Zn, Mn and Cd, and metals from the platinum and palladium families including Pd, Rh, Ru, Pt, Ir, Os and Re.

More specifically, plants which naturally concentrate nickel in above-ground tissues and generally exhibit an enhanced uptake of cobalt and other metals include members of the section Odontarrhena of the genus *Alyssum*. The metals accumulate in nickel-hyperaccumulating *Alyssum* plant species when the plants are grown in contaminated soils. Some 48 taxa within the section Odontarrhena of the genus *Alyssum* are known to be hyperaccumulators of nickel. These include the following species: *A. akamasicum*, *A. alpestre*, *A. anatolicum*,

30

5

20

25

A. callichroum, A. cassium, A. chondrogynum, A. cilicicum, A. condensatum, A. constellatum, A. crenulatum, A. cypricum, A. davisianum, A. discolor, A. dubertretii, A. eriophyllum, A. euboeum, A. floribundum, A. giosnanum, A. hubermorathii, A. janchenii, A. markgrafii, A. masmenaeum, A. obovatum, A. oxycarpum, A. penjwinensis, A. pinifolium, A. pterocarpum, A. robertianum, A. samariferum, A. singarense, A. smolikanum, A. syriacum, A. trapeziforme, A. troodii, A. virgatum, A. murale, A. pintodasilvae (also known as A. serpyllifolium var. lusitanicum), A. serpyllifolium, A. malacitanum (also known as A. serpyllifolium var. malacitanum), A. 1esbiacum, A. fallacinum, A. argenteum, A. bertolonii, A. tenium, A. heldreichii, A. corsicum, A. pterocarpum and A. caricum as well as newly discovered species such as A. corsicum G16, A. murale G69 and A. murale G82. These species were deposited on November 6, 1998, under the provisions of the Budapest Treaty at the American Type Culture Collection, 10801 University Blvd., Manassas, VA 20110-2209, and assigned ATCC nos. 203436, 203437 and 203438, respectively.

Species of Alyssum that naturally accumulate nickel in amounts of up to 20% greater than any known Alyssum hyperaccumulator have been isolated. Species A. murale G49, A. murale G54, A. murale G69 and A. murale G82 isolated in Greece and species A. corsicum G16 isolated in Turkey all accumulate nickel in amounts greater than the known species A. murale 103 which accumulates nickel such that nickel makes up 1.14% by dry weight of a plant shoot from a test field of serpentine soil. The new hyperaccumulators accumulate nickel in amounts such that 1.55-1.60% by dry weight of the shoot is nickel. The results of nickel accumulation of these five new accumulators relative to the benchmark accumulator A. murale 103 is shown in Example 4.

About 250 other plant taxa, including those of tropical origin, have been shown to accumulate quantities of nickel and other metals. However, many of these plants do not exceed about 10,000 mg of metal per kg of plant tissue dry weight. Other metal-accumulating plants includes species of the genus Cyanotis such as Cyanotis longifolia; species of the genus Bulbostylis such as Bulbostylis

10

15

30

mucronata; species of the genus Combretum such as Combretum decandrum; species of the genus Crassula such as C. alba, C. vaginata and C. argyrophylla; species of the genus Clethra such as Clethra barbinervis; plants from the Cunoniaceae family such as species of the genus Geissois including G. intermedia, G. magnifica, G. montana, G. pruinosa, G. trifoliata and G. racemosa; species of the genus Argophyllum; members of Brassicaceae family such as species of the genus Thlaspi such as Thlaspi caerulescens, Thlaspi montanum var. montanum and Thlaspi montanum var. siskiyouense; species of the genus Serpentine such as Serpentine polygaloides; species of the genus Sebertia such as Sebertia acuminata; species of the genus Hybanthus such as Hybanthus floribundas; species of the genus Psychotria such as Psychotria douarrei; species of the genus Rinorea such as Rinorea bengalensis; species of the genus Pearsonia such as Pearsonia metallifera; species of the genus Sebertia such as Sebertia acuminata; and species of the following genera: Homalium, Myristica, Trichospermum, Planchonella and Peltaria. Additional plants include, but are not limited to, Streptanthus polygaloides, Berkheya coddii, Phyllanthus palawanensis, Dichapetalum gelonioides ssp. tuberculatum and Stackhousia trvonii.

Additional metal hyperaccumulators are listed below:

20 ACANTHACEAE

Blepharis acuminata, Justicia lanstyakii, Lophostachys villosa, Phidiasia lindavii, Ruellia geminiflora

ADIANTACEAE

Adiantum sp.

25 ANACARDIACEAE

Rhus wildii

ASTERACEAE

Berkheya coddii, Chromolaena sp. cf. meyeri, Dicoma niccolifera, Gochnatia crassifolia, G. recurva, Koanophyllon grandiceps, K. prinodes, Leucanthemopsis alpina, Pentacalia, Senecio Senecio pauperculus, Shafera platyphylla, Solidago hispida

BORAGINACEAE

Heliotropium sp.

BRASSICACEAE

Bornmuellera, Cardamine resedifolia, Cochlearia aucheri, C. sempervivum, Peltaria emarginata, Streptanthus polygaloides

5

BUXACEAE

Buxus

CAMPANULACEAE

Campanula scheuchzeri, Arenaria, Minuartia laricifolia, M. verna

10

CLUSIACEAE

Garcinia bakeriana, G. polyneura, G. revoluta, G. ruscifolia

CONVOLVULACEAE

Merremia xanthophylla

CUNONIACEAE

15

Pancheria engleriana

DICHAPETALACEAE

Dichapetalum gelonioides and ssp. tuberculatum and ssp. andamanicum

DIPTEROCARPACEAE

Shorea tenuiramulosa

20

ESCALLONIACEAE

Argophyllum grunowii, A. laxum

EUPHORBIACEAE

Baloghia sp., Bonania, Cleidion viellardii, Cnidoscolus sp. cf. bahianus, Euphorbia, Gymnanthes recurva, Leucocroton, Phyllanthus, Sapium erythrospermum, Savia

25

FABACEAE

Anthyllis sp., Pearsonia metallifera, Trifolium pallescens

FLACOURTIACEAE

Casearia silvana, Homalium, Xylosma

30

JUNCACEAE

Luzula lutea

MELIACEAE

20

Walsura monophylla

MYRISTICACEAE

Myristica laurifolia

MYRTACEAE

Mosiera araneosa, M. ekmanii, M. x miraflorensis, M. ophiticola, Psidium araneosum, P. havanense

OCHNACEAE

Brackenridgea palustris and ssp. foxworthyi and ssp. kjellbergii, Ouratea nitida, O. striata

10 OLEACEAE

Chionanthus domingensis

ONCOTHECACEAE Oncotheca balansae

POACEAE

Trisetum distichophyllum

RANUNCULACEAE Ranunculus glacialis

RUBIACEAE

Ariadne shaferi ssp. shaferi and ssp. moaensis, Mitracarpus sp., Phyllomelia coronata, Psychotria clementis, P. costivenia, P. douarrei, P. glomerata, P. osseana, P. vanhermanii, Rondeletia

SAPOTACEAE

Planchonella oxyedra, Sebertia acuminata

SAXIFRAGACEAE

25 Saxifraga

SCROPHULARIACEAE

Esterhazya sp. and Linaria alpina

STACKHOUSIACEAE

Stackhousia tryonii

30 TILIACEAE

Tetralix brachypetalus, T. cristalensis, T. jaucoensis, T. moaensis, T. nipensis, Trichospermum kjellbergii

TURNERACEAE

Turnera subnuda

VELLOZIACEAE

Vellozia sp.

5 VIOLACEAE

Agatea deplanchei, Hybanthus, Rinorea bengalensis, R. javanica, Rinorea sp.

ACERACEAE

Acer pseudoplatanus

10 BRASSICACEAE

Cardaminopsis halleri, Thlaspi avalanum, T. brachypetalum, T. caerulescens, T. ochroleucum, T. rotundifolium subsp. cepaeifolium, T. praecox, T. stenopterum, T. tatrense

CARYOPHYLLACEAE

15 Minuartia verna, Polycarpaea synandra

CISTACEAE

Cistus incanus ssp. creticus

DICHAPETALACEAE

Dichapetalum gelonioides

20 PLUMBAGINACEAE

Armeria maritima var. halleri

POACEAE

Agrostis stolonifera, A. tenuis, Arrhenatherum elatius, Festuca ovina

POLYGONACEAE

25 Rumex acetosa

VIOLACEAE

Viola calaminaria

AMARANTHACEAE

Pandiaka metallorum, Celosia trigyna

30 ASTERACEAE

Anisopappus chinensis, A. davyi, Gutenbergia pubescens, Millotia myosotidifoliab, Vernonia petersii

CARYOPHYLLACEAE

Minuartia verna ssp. hercynica and Silene cobalticola

COMMELINACEAE

Commelina zigzag and Cyanotis longifolia

5 CONVOLVULACEAE

Ipomoea alpina

CRASSULACEAE

Crassula alba and C. vaginata

CYPERACEAE

10 Ascolepis metallorum, Bulbostylis cupricola, B. pseudoperennis

EUPHORBIACEAE

Monadenium cupricola and Phyllanthus williamioides

FABACAEAE

Crotalaria cobalticola and Vigna dolomitica

15 IRIDACEAE

Gladiolus gregarius

LAMIACEAE

Aeollanthus subacaulis var. linearis, A. homblei, A. saxatilis, A. subacaulis var. ericoides and var. linearis, Becium grandiflorum var. vanderystii, Haumaniastrum homblei, H. katangense, H. robertii, H. rosulatum

MALVACEAE

Hibiscus rhodanthus

PINACEAE

25 Abies balsamea

POACEAE

Eragrostis racemosa, Rendlia altera, Sporobolus congoensis

PTERIDACEAE

Actiniopteris sp.

30 SCROPHULARIACEAE

Alectra sessiliflora var. senegalensis, Buchnera henriquesii, Crepidorhopalon tenuisa, C. perennisa, Sopubia mannii, S. metallorum, S. neptunii, Striga hermontheca

TILIACEAE

Triumfetta dekindtiana, T. digitata, T. welwitschii var. descampii

VELLOZIACEAE

Xerophyta retinervis var. equisetoides

5 APOCYNACEAE

Alyxia rubricaulis

CELASTRACEAE

Maytenus bureaviana, M. pancheriana, M. sebertiana

CLUSIACEAE

10 Garcinia amplexicaulis

MYRTACEAE

Eugenia clusioides

PROTEACEAE

Beaupreopsis paniculata, Macadamia angustifolia, M. neurophylla

15 ASTERACEAE

Haplopappus fremontii, Machaeranthera glabriuscula, M. ramosa, M. venusta

BRASSICACEAE

Stanleya pinnata, S. bipinnata

20 CHENOPODIACEAE

Atriplex confertifolia

LECYTHIDACEAE

Lecythis ollaria

LEGUMINOSAE

25 Acacia cana, Astragalus bisulcatus, A. osterhoutii, A. pattersonii, A. pectinatus, A. racemosus, Neptunia amplexicaulis

RUBIACEAE

Morinda reticulata

30 SCROPHULARIACEAE

Castilleja chromosa

10

15

20

25

The metals accumulated include nickel, cobalt, barium, gold, beryllium, mercury, molybdenum, copper, arsenic, selenium, antimony, manganese, silver, thallium, tin, lead, rubidium, chromium, cerium, vanadium, cesium, uranium, plutonium, strontium, yttrium, technetium, iridium, ruthenium, palladium, rhodium, platinum, osmium, rhenium, zinc and cadmium.

Metal sequestration can be improved by optimizing soil calcium concentration, using ammonium-containing or ammonium-generating fertilizers rather than other nitrate-containing fertilizers, and by applying chelating agents to the soil in which the hyperaccumulator plants are grown.

Alyssum species which hyperaccumulate metals such as nickel and cobalt evolved in nickel-rich ultramafic and serpentine soils which have low soil calcium and a low Ca:Mg ratio. It is now known that the presence of extremely low and extremely high calcium concentrations in soil inhibits nickel hyperaccumulation by Alyssum. See PCT/US97/15109. Acceptable calcium concentrations in soil range from about 0.128 mM to about 5.0 mM. In terms of percentages, an acceptable calcium concentration in soil ranges from about 2% to about 80% of the exchangeable cations. A preferable range is from about 10% to about 80% of the exchangeable cations. The most preferred range is from about 30% to about 70% of the exchangeable cations. Such ranges can be achieved, if necessary, by adding calcium-containing agents to the soil such as limestone. In addition, gypsum could be added to the soil to raise the exchangeable calcium of the soil to benefit nickel accumulation.

The presence of intermediate concentrations of calcium, i.e., between about 0.128 mM and about 5.0 mM, increases nickel uptake whereas calcium values of about 0.128 mM and below, or about 5 mM and above, decrease nickel uptake. Combined with an exchangeable Ca:Mg ratio of between about 0.16 and about 0.40, much lower than recommended, an additional increase in nickel concentration in plant tissues is observed. By "exchangeable Ca:Mg ratio" is intended the ratio of extractable calcium and magnesium in the soil.

20

5

10

25

Although hyperaccumulators such as Alyssum have developed the ability to hyperaccumulate metals in above-ground tissues, fertilizer supportive of growth, particularly in polluted soil, can be used as an additive to increase hyperaccumulation. Ammonium fertilizers localize acidification adjacent to the root which aids hyperaccumulation of various metals such as Ni, Zn, Cd, Co, etc. The use of ammonium fertilizers per se is well-known, and acceptable fertilizers and protocols can be readily determined with no more than routine experimentation, by those of ordinary skill in the art. Other additives include, but are not limited to, nutrients such as phosphate which helps to maximize the yield of nickel, for example.

Another possible additive to the contaminated soil is a metal chelating agent. Metal chelates are commonly used in agriculture and occur naturally in living cells. The addition of chelating agents, such as nitrolotriacetic acid (NTA), ethylenediam in etetra a cetic acid (EDTA), ethyleneglycol-bis-(p-aminoethylether-N, N-tetraacetic acid) or any of a variety of amino-acetic acids known to those of ordinary skill in the art as chelating agents, to the soil to be phytomined or phytoextracted improves the movement of soil metals to root surfaces for uptake and translocation into above-ground tissues. Preferred chelating agents are NTA or EDTA. Typically, chelating agents will be added at a concentration ranging from about 0.5 to about 10 millimoles per kg soil. As with the use of fertilizers, the optimum concentration of chelating agents can be readily determined with no more than routine experimentation. Chelating compounds which chelate nickel in the presence of high soil levels of Fe, Mg and Ca selectively increase nickel uptake by hyperaccumulator plants.

The following examples are illustrative, but not limiting, of the methods of the present invention. Other suitable modifications and adaptations of the variety of conditions normally encountered which are obvious to those skilled in the art are within the spirit and scope of the present invention.

10

15

Examples

Example 1

A. murale 103 plants were grown in sets of two for 120 days in 19 pot-sets (4 L) of contaminated or serpentine soils (Mg-nitrate was leached out) without acidification, the first pot in a set, and with acidification, the second pot in a set. Water was maintained near field capacity by daily watering with deionized water. The plants were cultivated at a temperature of about 28°C during the day and about 20°C at night. The soils were acidified using nitric acid and the pH was raised using powdered reagent-grade CaCO₃. The soils included serpentine soils rich in nickel (containing from about 100 to about 5000 ppm nickel) obtained from southwest Oregon (soils 3-19), nickel-refinery contaminated Welland loam from Port Colborne, Ontario (soil 1) and nickel-refinery contaminated Quarry muck from Port Colborne, Ontario (soil 2). Fertilizers containing, inter alia, nickel, potassium, sulfur and phosphorous, were added to optimize plant growth.

Table 1 shows the results of the experiment in contaminated soil.

Table 1

Soil	TRT	Final pH	Yield	Ni	Со	Mn	Zn	Cu	Fe	
	·		g shoot dry matter/ pot	mg/kg						
1	2	5.16	27.4	9150	119	82.4	117	15.0	58	
1	6	4.96	22.7	4220	84.7	145.6	180	19.5	64	
2	2	6.04	40.9	4570	5.9	20.9	99.0	4.0	68	
2	6	5.40	28.8	2150	7.1	63.0	142	6.5	82	
3	2	6.26	21.5	6370	19.9	68.8	61.5	3.5	160	
3	6	5.38	19.7	6480	308	680	65.9	5.5	260	
4	2	5.61	19.6	12400	56.5	181	88.0	4.0	332	
4	6	5.21	15.6	8560	377	140	135	5.0	345	
5	2	5.88	24.0	1860	6.0	53.0	252	3.2	137	
5	6	5.32	21.1	1220	9.8	153	379	3.5	121	
6	2	6.03	24.5	4580	14.6	84.2	61.2	5.2	183	
6	6	5.42	27.2	5040	58.5	227	70.3	5.5	195	
7	2	5.54	23.3	5750	36.3	134	83.7	5.0	250	
7	6	5.28	23.2	4870	86.8	272	77.9	5.5	274	
8	2	5.77	21.1	9630	28.8	130	52.6	4.0	223	
8	6	5.21	17.5	7180	94.0	291	74.9	4.8	221	
9	2	6.12	22.1	9770	38.7	122	69.6	4.8	240	
9	6	5.62	22.5	9100	196	532	69.7	5.2	273	
10	2	6.25	20.0	12900	31.2	109	79.3	2.5	318	
10	6	5.76	19.3	11500	182	774	93.5	3.2	412	
11	2	5.72	32.8	8460	37.3	148	75.5	5.0	266	
11	6	5.35	24.3	6010	136	339	93.6	4.8	230	
12	2	6.54	20.3	8070	29.0	84.4	74.0	3.5	222	
12	6	5.78	18.4	8240	86.0	186	66.5	3.2	178	
13	2	6.34	18.8	11000	16.2	39.1	51.8	2.2	186	
13	6	5.87	19.6	9970	36.0	103	56.6	2.8	181	
14	2	5.68	21.3	9150	67.0	331	65.8	4.8	278	

10

15

Soil	TRT	Final pH	Yield	Ni	Co	Mn	Zn	Cu	Fe
			g shoot dry matter/ pot	mg/kg					
14	6	4.84	13.3	5820	313	957	86.0	4.8	567
15	2	6.04	19.4	7620	30.5	142	69.8	4.8	365
15	6	5.94	23.7	6110	463	820	88.6	4.8	220
16	2	6.07	21.0	3090	47.4	128	89.1	6.8	172
16	6	5.41	18.2	3560	225	563	105	8.0	267
17	2	6.02	20.6	9080	37.5	124	114	3.8	256
17	6	5.63	23.9	7940	262	973	127	4.2	252
18	2	5.99	19.4	11600	35.3	127	68.5	3.0	440
18	6	5.53	15.4	9500	204	908	116	4.2	548
19	2	5.59	21.8	436	19.1	259	92.4	7.8	190
19	6	5.11	19.5	584	72.4	929	112	8.8	156

"TRT" = treatment. In treatment 2, the soil pH was not adjusted. In treatment 6, the soil pH was acidified.

As illustrated in Table 1, the plants grown on soils of less acidic pH generally accumulated far greater amounts of nickel than the plants grown on more acidic soils. In addition, plants taking up larger amounts of nickel on less acidic soils accumulated smaller amounts of other metals such as cobalt, manganese and zinc which are commonly found in lower concentrations in shoots after soil pH is raised.

20 Example 2

To validate the above example and to obtain optimization, *Alyssum* plants were grown on nickel-refinery contaminated Welland loam (soil 1), wherein the pH was elevated by applying limestone (Table 2). The plants were also grown on nickel-refinery contaminated Quarry muck (soil 2) and serpentine soils (soils 3-

11) (Table 3). The same cultivation conditions recited in Example 1 were used in Example 2.

5	

	10
Į.	10

Soil	TRT	Yield	Ni	Со	Mn	Zn
		g/pot	g/kg	mg/kg	mg/kg	mg/kg
1	1	6.68 b*	7.61 a	127 a	23.7 e	157 fg
Phospha	te Series:					
1	3	7.82 ab	5.94 bc	118 ab	72.8 c	209 ab
1	2	9.78 ab	5.49 cd	109 bcd	59.3 d	170 def
1	4	8.71 ab	6.40 b	114 a-d	66.7 cd	178 c-f
1	5	8.03 ab	5.97 bc	98.8 d	60.8 cd	169 def
pH Serie	es:					
1	6	8.14 ab	3.93 e	132 a	177 a	217 a
1	7	7.46 ab	4.93 d	119 ab	99.8 b	183 b-e
1	2	9.78 ab	5.49 cd	109 bcd	59.3 d	170 deg
1	8	10.4 a	8.47 a	101 cd	19.1 f	142 g
Ca:Mg	Series:					
1	9	9.22 ab	6.10 bc	119 ab	67.3 cd	168 ef
1	2	9.78 ab	5.49 cd	109 bcd	59.3 d	170 def
1	10	7.80 ab	5.55 cd	117 abc	64.7 cd	198 abc
1	11	8.72 ab	5.85 bc	120 ab	69.8 cd	195 a-d

^{*}a-g indicate means followed by the same letter are not significantly different at the P < 0.05 level according to the Duncan-Walker K-ratio t-test.

[&]quot;TRT" = treatment

Table 3

Effect of soil treatments on soil pH and micronutrient composition of *Alyssum murale* and *Alyssum corsicum* grown on nickel-refinery contaminated Welland loam (soil 1), nickel-refinery contaminated Quarry muck (soil 2) and serpentine soils (soils 3-11) for 120 days.

Soil	TRT	Final pH	Cu	Zn	Со	Ni	Mn	Fe
			mg/kg	mg/kg	mg/kg	g/kg	mg/kg	mg/kg
1		5.47	11.0	156	136	8.13	39.2	67.6
Phosph fertiliz	nate Series (pho er):	sphate adde	ed to the soi	l in kg/ha b	y the addition	on of phospl	nate-contain	ing
3	0 P	5.23	15.0	179	99.1	7.58	56.2	49.6
2	100 P	5.18	16.0	131	102	7.34	59.7	50.1
4	250 P	5.24	14.5	133	82.2	7.37	56.8	56.4
5	500 P	5.13	14.5	129	73.8	6.50	53.1	50.8
pH Sei	ies (soil was ac	idified usin	g nitric acid	for "Lo pH	[" and "ML	o pH"):		
6	Lo pH	4.99	19.2	192	91.0	4.16	129	53.1
7	MLo pH	5.18	16.8	160	104	5.77	81.2	64.0
2	As is pH	5.18	16.0	131	102	7.34	59.7	50.1
8	Limed	5.57	10.1	102	71.1	9.28	19.9	57.6
Ca:Mg	Ratio Series:							
9	1.0 Ca	5.25	17.0	134	108	7.32	65.0	55.0
2	0 Ca/Mg	5.18	16.0	131	102	7.34	59.7	50.1
10	2.5 Mg	5.13	17.4	152	90.4	6.75	48.9	53.0
11	5.0 Mg	5.04	16.2	149	87.6	5.71	54.8	67.1

[&]quot;TRT" = treatment

10

5

15

20

[&]quot;MLo pH" = medium-low pH

The soil designations correspond to the soil designations in Example 1.

The "pH series" experiments demonstrate that the application of limestone increases the uptake of nickel in *Alyssum* so that plant tissues accumulate an increased concentration of nickel.

Example 3

5

The results show an increase in the geometric mean of nickel uptake in plant tissue by liming *Alyssum* plants cultivated on nickel-refinery contaminated Quarry muck (soil 2) (Table 4) and on nickel-refinery contaminated Welloam loam (soil 1), nickel-refinery contaminated Quarry muck (soil 2) and selected serpentine soils (soils 3-11) (Table 5) from Example 1. The cultivation conditions were the same as those for Examples 1 and 2.

Soil	TRT	Treatment	Shoot Yld	Shoot Ni	Shoot Co	Shoot MN
			g/pot	g/kg	mg/kg	mg/kg
2	1	None	8.46 d*	3.33 abc	8.62 ab	27.9 bc
Phosphate	Series:					
2	3	0 P	10.78 a-d	3.24 bc	5.50 b	15.0 bc
2	2	100 P	12.09 a	3.23 bc	5.75 ab	14.5 bc
2	4	250 P	11.53 abc	3.76 a	5.50 b	18.6 bc
2	2	500 P	11.86 ab	3.30 abc	6.38 ab	27.7 bc
pH Series						
2	6	Lo pH	12.01 ab	1.48 e	10.25 a	59.8 a
2	7	Med pH	9.44 bcd	2.12 d	6.12 ab	29.0 b
2	2	As is pH	12.09 a	3.23 bc	5.75 ab	14.5 bc
2	8	Limed	11.14 abc	3.72 ab	5.88 ab	13.3 с
Ca:Mg Se	ries:					
2	9	Ca	9.08 cd	3.42 abc	6.38 ab	16.3 bc
2	2	As is Ca	12.09 a	3.23 bc	5.75 ab	14.5 bc
2	10	Med Mg	11.66 ab	3.03 c	4.62 b	24.9 bc
2	11	Hi Mg	9.98 a-d	2.94 c	5.25 b	23.3 bc

^{*}a-e indicate means followed by the same letter are not significantly different at the P < 0.05 level according to the Duncan-Walker K-ratio t-test.

5

20

[&]quot;TRT" = treatment

15

20

5

Effect of altering nickel-refinery contaminated Welland loam (soil 1), nickel-refinery contaminated Quarry muck (soil 2) and serpentine soils (soils 3-11) by adding phosphate, adjusting the pH or adjusting the Ca:Mg ratio on soil pH, mean yield and micronutrient composition of shoots of *Alyssum* species grown for 120 days (GM designates geometric mean).

Soil	TRT	Final pH	GM- Yield	GM-Nı	GM-Co	GM-Mn	GM-Zn	GM-Fe	GM- Cu
			g/pot			mg/l	ιg		
1	None	6.34	20.2	5460	7.6	11.9	151	61	4.8
	phate Treat izer):	tments (phos	phate add	ed to the so	il in kg/ha	by the addit	tion of pho	sphate-cont	aining
3	0 P	6.09	41.6	4400	5.8	16.5	152	56	4.2
2	100 P	6.05	42.7	4120	5.7	18.6	126	57	4.5
4	250 P	6.07	49.9	4120	5.1	21.4	143	57	4.8
5	500 P	5.98	46.4	3800	5.1	22.9	139	54	4.2
pH]	reatments	(soil was aci	dified usir	ng nitric aci	d for "Lo p	H" and "M	ed-pH"):		
6	Lo pH	5.44	32.2	2010	6.8	50.5	153	68	6.4
7	Med- pH	5.76	36.1	2700	4.5	21.0	143	60	4.8
2	As is pH	6.05	42.7	4120	5.7	18.6	126	57	4.5
8	Limed	6.20	40.5	4520	6.3	15.8	137	55	4.1
Ca:N	Mg Treatme	ents:							
9	0.0 Ca	6.13	38.6	4510	6.3	16.2	135	57	4.8
2	1.0 Ca	6.05	42.7	4120	5.7	18.6	126	56	4.5
10	2.5 Mg	5.98	39.0	4410	5.9	16.2	146	63	4.6
11	5.0 Mg	5.91	44.0	4260	5.8	18.3	158	58	4.6

25 "TRT" = treatment

The soil designations correspond to the soil designations in Example 1.

Example 4 - Novel Hyperaccumulators

The concentration of elements in the shoots of *Alyssum* species grown on a field of serpentine colluvial soil in Josephine County, Oregon, are shown in Table 6 below.

5

10

Table 6

Row	Species	Genotype	Block	Zn	P	Cu	Co	Ni	Mn	Fe	Mg	Ca	K
	l. corsicum							13400					
483 A	l. corsicum	16	2	141	4.08	8	16	17500	32	755	5.99	24.2	44.3
129 A	1. murale	49	1	99	4.80	7	12	14100	41	397	3.98	32.1	41.4
325 A	1. murale	49	2	106	4.63	8	16	17100	46	455	5.32	31.7	41.7
135 A	1. murale	54	1	119	4.18	5	13	15600	53	927	4.02	25.8	44.5
143 A	1. murale	69	1	165	5.78	5	16	16700	53	380	4.52	17.3	38.8
553 A	1. murale	69	2	191	4.97	6	15	13400	45	616	5.66	25.4	6.16

The elements are present in mg/kg amounts.

20

15

Whole shoots or side branch samples containing stems and leaves were collected from pots or the field for each genotype, dried in forced air drying ovens and ground with a non-contaminating mill to less than about 0.1 mm. The ground samples were then placed in a borosilicate beaker and ashed at 480°C overnight. Nitric acid was added to dissolve the resultant ash which was then heated until dry on a hot plate. Hydrochloric acid (3.0 M) was added and the beaker was refluxed for two hours to determine recovered nickel concentration. Concentrations of nickel were measured by an inductively coupled argon plasma emission spectrometer. Low concentrations were measured by atomic absorption spectrometry.

25

This invention has been described in specific detail with regard to specific plants and methods for increasing metal, such as nickel, uptake via phytomining or phytoextraction. Except where necessary for operability, no limitation to these

specific materials is intended nor should such a limitation be imposed on the claims appended hereto. From the foregoing description, one skilled in the art can easily ascertain the essential characteristics of this invention, and without departing from the spirit and scope thereof, can make various changes and modifications of the invention to adapt it to various usages and conditions without undue experimentation. All patents, patent applications and publications cited herein are incorporated by reference in their entirety.

5

What Is Claimed Is:

1./

A method for selectively increasing the amount of at least one metal recovered from metal-containing soil comprising:

- (a) elevating the pH of the soil; and
- (b) cultivating at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate said at least one metal from the soil in above-ground tissue.
- 2. The method of claim 1, wherein said at least one metal is nickel.
- 3. The method of claim 1, wherein the pH of the soil is elevated by adding to the soil at least one agent that results in an increase in the soil pH.
- 4. The method of claim 3, wherein the at least one agent that results in an increase in the soil pH is selected from the group consisting of limestone, dolomitic limestone, lime, hydrated lime, limestone equivalents and mixtures thereof.
- 5. The method of claim 1, further comprising after said cultivating:
 - (c) lowering the pH of the soil; and
 - (d) cultivating the at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate at least one second metal from the soil in above-ground tissue.
 - 6. The method of claim 5, wherein the at least one second metal is selected from the group consisting of: cobalt, palladium, rhodium, ruthenium, platinum, iridium, osmium, rhenium and mixtures thereof.

20

- 7. The method of claim 5, wherein the pH of the soil is lowered by adding to the soil at least one agent that results in a decrease of the soil pH.
- 8. The method of claim 1, wherein said at least one plant is an *Alyssum* plant.

9. The method of claim 8, wherein said Alyssum plant is selected from the group consisting of: A. murale, A. pintodasilvae, A. serpyllifolium, A. malacitanum, A. 1esbiacum, A. fallacinum, A. argenteum, A. bertolonii, A. tenium, A. heldreichii, A. corsicum, A. pterocarpum, A. caricum and mixtures thereof.

10.

A method for recovering nickel from nickel-containing soil comprising:

- (a) elevating the pH of the soil;
- (b) cultivating at least one nickel-hyperaccumulator plant in the soil under conditions such that at least 0.1% of the above-ground tissue of said at least one plant, on a dry weight basis, is nickel;
- (c) harvesting said at least one plant; and
- (d) recovering nickel from said harvested plant.
- 11. The method of claim 10, wherein the soil has a calcium concentration of between about 20-80%.
- 12. The method of claim 10, wherein the nickel is recovered by drying and combusting the harvested plant to oxidize and vaporize organic material present.
- 13. The method of claim 10, wherein said at least one plant is an *Alyssum* plant.

15

5

10

- 14. The method of claim 13, wherein said Alyssum plant is selected from the group consisting of: A. murale, A. pintodasilvae, A. serpyllifolium, A. malacitanum, A. lesbiacum, A. fallacinum, A. argenteum, A. bertolonii, A. tenium, A. heldreichii, A. corsicum, A. pterocarpum, A. caricum and mixtures thereof.
- 15. The method of claim 14, wherein said *Alyssum* plant is selected from the group consisting of: *A. corsicum G16*, *A. murale G69*, *A. murale G82* and mixtures thereof.
- 16. The method of claim 10, wherein at least about 2.5% of the above-ground tissue of said at least one plant, on a dry weight basis, is nickel.
- 17. The method of claim 16, wherein at least about 3.0% of the above-ground tissue of said at least one plant, on a dry weight basis, is nickel.
- 18. The method of claim 17, wherein about 4.0% of the above-ground tissue of said at least one plant, on a dry weight basis, is nickel.

A method for recovering cobalt from cobalt-containing soil comprising:

- (a) lowering the pH of the soil;
- (b) cultivating at least one cobalt-hyperaccumulator plant in the soil under conditions such that at least 0.1% of the above-ground tissue of said at least one plant, on a dry weight basis, is cobalt;
- (c) harvesting said at least one plant; and
- (d) recovering cobalt from said harvested plant.
- 20. The method of claim 19, wherein the soil has a calcium concentration of between about 20-80%.

10

5

15

15

5

- 21. The method of claim 20, wherein said at least one plant is an *Alyssum* plant.
- 22. The method of claim 21, wherein said Alyssum plant is selected from the group consisting of: A. murale, A. pintodasilvae, A. serpyllifolium, A. malacitanum, A. 1esbiacum, A. fallacinum, A. argenteum, A. bertolonii, A. tenium, A. heldreichii, A. corsicum, A. pterocarpum, A. caricum and mixtures thereof.

An isolated *Alyssum* plant species that accumulates nickel in quantities greater than that accumulated by *A. murale 103*.

An isolated *Alyssum* plant species cultivated on nickel-containing soil that accumulates nickel in above-ground tissue at a concentration of 1.55% or greater by weight based on the gross dry weight of said tissue.

- 25. The isolated *Alyssum* plant species of claim 23 or 24, wherein the species is *A. corsicum G16*.
- 26. The isolated *Alyssum* plant species of claim 23 or 24, wherein the species is *A. murale G69*.
 - 27. The isolated *Alyssum* plant species of claim 23 or 24, wherein the species is *A. murale G82*.
 - 28. Pollen of the plant of claim 23 or 24.
- 29. A plant having all the physiological and morphological characteristics of the plant of claim 23 or 24.

5

30. Propagation material of the plant of claim 23 or 24.

31/.

An *Alyssum corsicum G16* seed as deposited with the American Type Culture Collection under accession number 203436.

32.

An *Alyssum murale G69* seed as deposited with the American Type Culture Collection under accession number 203437.

33/.

An *Alyssum murale G82* seed as deposited with the American Type Culture Collection under accession number 203438.

- 34. A plant produced by growing the seed of any one of claims 31-33.
- 35. Pollen of the plant of claim 34.
- 36. A plant having all the physiological and morphological characteristics of the plant of claim 34.
- 37. Propagation material of the plant of claim 34.

38/.

A method for decontaminating metal-containing soil, comprising cultivating at least one hyperaccumulator plant in metal-containing soil, whereby the concentration of metal in the above-ground plant tissue of said at least one hyperaccumulator plant exceeds the concentration of metal in said soil by a factor of at least 2.

39. The method of claim 38, wherein the at least one hyperaccumulator plant exceeds the concentration of metal in said soil by a factor of 3.

40. The method of claim 39, wherein the at least one hyperaccumulator plant exceeds the concentration of metal in said soil by a factor of 4.



A method for selectively increasing the amount of at least one metal recovered from metal-containing soil comprising:

- (a) lowering the pH of the soil; and
- (b) cultivating at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate said at least one metal from the soil in above-ground tissue.
- 42. The method of claim 41, wherein said at least one metal is selected from the group consisting of: cobalt, palladium, rhodium, ruthenium, platinum, iridium, osmium, rhenium and mixtures thereof.
- 43. The method of claim 41, wherein the pH of the soil is lowered by adding to the soil at least one agent that results in a decrease of the soil pH.
- 44. The method of claim 41, further comprising after said cultivating:
 - (c) raising the pH of the soil; and
 - (d) cultivating the at least one metal-hyperaccumulator plant in the soil under conditions sufficient to permit said at least one plant to accumulate at least one second metal from the soil in above-ground tissue.
- 45. The method of claim 44, wherein the pH of the soil is elevated by adding to the soil at least one agent that results in an increase in the soil pH.
- 46. The method of claim 45, wherein the at least one agent that results in an increase in the soil pH is selected from the group consisting of limestone, dolomitic limestone, lime, hydrated lime, limestone equivalents and mixtures thereof.

10

5

15

47. The method of claim 44, wherein the at least one second metal is nickel.

Recovering Metals from Soil

Abstract

The invention relates to recovering metals, such as nickel and cobalt, by phytomining or phytoextracting soils rich in metals wherein the desired metal is selectively accumulated in hyperaccumulator plants by adjusting the soil pH. The metals are ultimately recovered from above-ground plant tissues at economically acceptable levels without further contaminating the metal-containing sites. The invention also relates to metal-hyperaccumulating plants.

P.\USERS\kvidovic\1797\0090005\A269-45.wpd